



# BADAFLEX® | UL TPE-S 40A FR01

(TPE-SEBS)-FR

Injection moulding grade Styrene-Ethylen-/Butadien-Styrene Copolymer; UL listed halogenated flame retardant V0 according to RoHS standard

Properties	Test conditions	Test method	Unit	dry as molded
<b>Physical properties</b>				
Hardness		DIN ISO 7619-1 DIN ISO 7619-1	Shore A Shore D	40 -
Density		ISO 1183	g/cm <sup>3</sup>	1.30
Overmolding capability				PP
<b>Mechanical Properties</b>				
Tensile Strength	Parallel, 200 mm/min Across, 200 mm/min	DIN 53504 DIN 53504	MPa MPa	4.5 6
Elongation at break	Parallel, 200 mm/min Across, 200 mm/min	DIN 53504 DIN 53504	% %	650 700
Tear Strength	Parallel Across	DIN ISO 34 DIN ISO 34	N/mm N/mm	9 -
Abrasion loss		DIN ISO 4649	mm <sup>3</sup>	-
<b>Thermal Properties</b>				
Compression set	23 °C/72 h 70 °C/24 h 100 °C/24 h	DIN ISO 815-1 DIN ISO 815-1 DIN ISO 815-1	% % %	31 40 70
Thermal conductivity	Test plate 2 mm	DIN 52612-1	W/(m*K)	-
Flammability		UL94 UL94 UL94 UL94	Wall thickness Rating Wall thickness Rating	0,4 V-0 3,0 V-0
Glow wire test GWIT		IEC-60695-2-13 IEC-60695-2-13 IEC-60695-2-13 IEC-60695-2-13	Wall thickness mm Temperature °C Wall thickness mm Temperature °C	- - - -
Glow wire test GWFI		IEC-60695-2-12 IEC-60695-2-12 IEC-60695-2-12 IEC-60695-2-12	Wall thickness mm Temperature °C Wall thickness mm Temperature °C	- - - -
<b>Electrical Properties</b>				
Spec. Volume Resistivity		IEC-62631-3-1	Ohm*cm	-
Spec. Surface Resistivity		IEC-62631-3-2	Ohm	-
<b>Other Data</b>				
Melt volume rate (MVR)	Value Temperature Test load	ISO 1133 ISO 1133 ISO 1133	cm <sup>3</sup> /10min °C kg	- - -



# BADAFLEX® | UL TPE-S 40A FR01

(TPE-SEBS)-FR

Injection moulding grade Styrene-Ethylen-/Butadien-Styrene Copolymer; UL listed halogenated flame retardant V0 according to RoHS standard

Properties	Test conditions	Test method	Unit	dry as molded
<b>Processing injection molding</b>				
Melt temperature			°C	190 - 220
Mold temperature			°C	20 - 40
Guide Value Moisture			%	< 0.1
Drying temperature			°C	60 - 70
Guide Value Drying time			h	2 - 3

Issue date 17.01.2019

**LEGEND**

- not tested  
NB = No break

Based on our current state of knowledge, this data represents reference values and, unless otherwise stated, stands for uncoloured material. Therefore, it does not constitute a warranty of certain properties, more particularly it is no material specification. It is the responsibility of the processors to check the suitability of the material for a particular application as well as compliance with statutory regulations and intellectual property rights. The data stated above may be modified at any time without prior notice. The information does not imply any contractual obligation on our part, any liability is expressly excluded.