



<b>Badadur® PBT8</b>				
PBT Medium viscosity, standard injection moulding grade with good mechanical properties				
Properties	Test Conditions	Test Methods	Units	Typical Values
<b>Mechanical Properties</b>				
Tensile Modulus <sup>1</sup>	23° C, 1 mm/Min	ISO 527-1/2	MPa	2650
Yield Stress <sup>1</sup>	23° C, 50 mm/Min	ISO 527-1/2	MPa	57
Yield Strain <sup>1</sup>	23° C, 50 mm/Min	ISO 527-1/2	%	4
Nominal Stress at Break <sup>1</sup>	23° C, 50 mm/Min	ISO 527-1/2	%	>50
Stress at Break <sup>1</sup>	23° C, 5 mm/Min	ISO 527-1/2	MPa	*
Strain at Break <sup>1</sup>	23° C, 5 mm/Min	ISO 527-1/2	%	*
Bending Strength <sup>2</sup>	23° C	ISO 178	MPa	85
Charpy Impact Strength, unnotched <sup>2</sup>	23° C	ISO 179/1eU	kJ/m2	KB
	-30° C	ISO 179/1eU	kJ/m2	KB
Notched Charpy Impact Strength <sup>2</sup>	23° C	ISO 179/1eA	kJ/m2	5
	-30° C	ISO 179/1eA	kJ/m2	4
Izod notched Impact Strength <sup>2</sup>	23° C	ISO 180/1A	kJ/m2	5
	-30° C	ISO 180/1A	kJ/m2	4
<b>Thermal Properties</b>				
Melting Temperature <sup>3</sup>	10 K/Min	ISO 3146	°C	223
Temperature of Deflection under Load <sup>4</sup>	0,45 MPa	ISO 75-1/2	°C	160
	1,8 MPa	ISO 75-1/2	°C	60
Coefficient of Linear Thermal Elongation <sup>5</sup>	parallel direction	DIN 53752	E-4/K	1,35
	transverse direction	DIN 53752	E-4/K	1,35
Maximum Service Temperature	some hours	-	°C	160
	20 000 h 50 % Decrease in Tensile Strength or Yield Stress	IEC 216	°C	120
Flammability <sup>6</sup>	0,8 mm	UL 94	Class	HB
	1,6 mm	UL 94	Class	HB
Glow Wire Test	0,75 mm / 1,6 mm	GWIT	IEC-60695-2-13	-
	0,75 mm / 1,6 mm	GWFI	IEC-60695-2-12	-
<b>Electric Properties</b>				
Relative Permittivity <sup>7</sup>	1 MHz	IEC 250	-	3,2
Dissipation Factor <sup>7</sup>	1 MHz	IEC 250	E-4	180
Specific Volume Resistivity <sup>7</sup>	-	IEC 93	Ohm cm	>10 <sup>16</sup>
Specific Surface Resistivity <sup>7</sup>	-	IEC 93	Ohm	>10 <sup>14</sup>
Dielectric Strength <sup>7</sup>	-	IEC 243-1	kV/mm	24
Comparative Tracking Index	-	IEC 112	V	600
<b>Other data</b>				
Water Absorption	23° C, Saturation	ISO 62	%	0,5
Moisture Absorption	23° C, 50 % r.H.	ISO 62	%	0,2
Melt Volume Rate (MVR)	250° C/2,16kg	ISO 1133	cm <sup>3</sup> /10 min	-
Density	23° C	ISO 1183	g/ccm	1,31
<b>Processing</b>				
Melt Temperature	-	-	°C	240 – 260
Tool Surface Temperature	-	-	°C	60 – 100
Drying Temperature	-	-	°C	110 - 130
Drying Time	-	-	h	2 – 4h

**LEGEND:**

- <sup>1</sup> Test Specimen according to ISO 3167, Type A
- <sup>2</sup> Standard bar (80 x 10 x 4) mm
- <sup>3</sup> Compound for moulding
- <sup>4</sup> Standard bar (110 x 10 x 4) mm
- <sup>5</sup> Specimen (≥ 10 x 10 x 4) mm
- <sup>6</sup> Standard bar [125 x 13 x 0,8(1,6)] mm
- <sup>7</sup> Bar (80 x 80 x 1) mm
- <sup>8</sup> Specimen (≥ 15 x 15 x 4) mm

- \* not relevant
- not tested
- NB = No break

These data are typical values and represent the state of our knowledge at issue date. If not otherwise stated, the data is related to uncoloured material. They must not be construed as specification limits or as a guarantee for specific properties.  
It is the liability of the processor to test the suitability of the material for a specific application.

Issue date: 2008-09-15