



Badamid® LA70 GF25 HH					
PA66-GF25					
25% glass fibres reinforced, heat stabilised injection moulding grade for housing with high stiffness and good dimensional stability					
Properties	Test Conditions	Test Methods	Units	Dry as moulded	conditioned 23° C, 50% r.H.
Mechanical Properties					
Modulus of Elasticity, tensile	23° C, 1 mm/Min	ISO 527-1/2	MPa	8600	*
Yield Stress ¹	23° C, 50 mm/Min	ISO 527-1/2	MPa	*	*
Yield Strain ¹	23° C, 50 mm/Min	ISO 527-1/2	%	*	*
Nominal Stress at Break ¹	23° C, 50 mm/Min	ISO 527-1/2	%	*	*
Stress at Break ¹	23° C, 5 mm/Min	ISO 527-1/2	MPa	170	*
Strain at Break ¹	23° C, 5 mm/Min	ISO 527-1/2	%	2,8	*
Bending Strength ²	23° C	ISO 178	MPa	245	-
Charpy Impact Strength, unnotched ²	23° C	ISO 179/1eU	kJ/m2	56	*
	-30° C	ISO 179/1eU	kJ/m2	-	-
Notched Charpy Impact Strength ²	23° C	ISO 179/1eA	kJ/m2	8	*
	-30° C	ISO 179/1eA	kJ/m2	-	-
Izod notched Impact Strength ²	23° C	ISO 180/1A	kJ/m2	-	*
	-30° C	ISO 180/1A	kJ/m2	-	-
Thermal Properties					
Melting Temperature ³	10 K/Min	ISO 3146	°C	260	*
Temperature of Deflection under Load ⁴	0,45 MPa	ISO 75-1/2	°C	250	*
	1,8 MPa	ISO 75-1/2	°C	-	*
Coefficient of Linear Thermal Elongation ⁵	parallel direction	DIN 53752	E-4/K	-	*
	transverse direction	DIN 53752	E-4/K	-	*
Maximum Service Temperature	some hours	-	°C	-	*
	20 000 h 50 % Decrease in Tensile Strength or Yield Stress	IEC 216	°C	-	*
Flammability ⁶	0,8 mm	UL 94	Class	HB	*
	1,6 mm	UL 94	Class	HB	*
Glow Wire Test	0,75 mm / 1,6 mm	GWIT	IEC-60695-2-13	*	*
	0,75 mm / 1,6 mm	GWFI	IEC-60695-2-12	*	*
Electric Properties					
Relative Permittivity ⁷	1 MHz	IEC 250	-	3,5	-
Dissipation Factor ⁷	1 MHz	IEC 250	E-4	140	-
Specific Volume Resistivity ⁷	-	IEC 93	Ohm cm	10 ¹³	-
Specific Surface Resistivity ⁷	-	IEC 93	Ohm	10 ¹²	-
Dielectric Strength ⁷	-	IEC 243-1	kV/mm	-	-
Comparative Tracking Index	-	IEC 112	V	550	-
Other data					
Water Absorption	23° C, Saturation	ISO 62	%	5,8	*
Moisture Absorption	23° C, 50 % r.H.	ISO 62	%	2	*
Density	23° C	ISO 1183	g/ccm	1,32	*
Processing					
Melt Temperature	-	-	°C	280-300	*
Tool Surface Temperature	-	-	°C	80-90	*
Drying Temperature	-	-	°C	80	*
Drying Time	-	-	h	2-4	*

LEGEND:

¹ Test Specimen according to ISO 3167, Type A

² Standard bar (80 x 10 x 4) mm

³ Compound for moulding

⁴ Standard bar (110 x 10 x 4) mm

⁵ Specimen (≥ 10 x 10 x 4) mm

⁶ Standard bar [125 x 13 x 0,8(1,6)] mm

⁷ Bar (80 x 80 x 1) mm

⁸ Specimen (≥ 15 x 15 x 4) mm

* not relevant

- not tested

NB = No break

These data are typical values and represent the state of our knowledge at issue date. If not otherwise stated, the data is related to uncoloured material. They must not be construed as specification limits or as a guarantee for specific properties. It is the liability of the processor to test the suitability of the material for a specific application.

Issue date: 2010-02-11